

No.	Size	Thickness	Grade	Finish	Length	Quantity		Chemical Composition (%)								Mechanical Test				Heat number
	(MM)	(MM)		(GRIT)	(MM)	(Tubes)	(M)	C	Si	Mn	P	S	Ni	Cr	Cu	T.S (Rm) N/m m ²	Elongation (%)	Y.S(Rp) 0.2%N/m m ²	Hardness (HV)	
19	50.80	1.37	201	600	6,000	58	348	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	553	63	299	226	MG02072508
20	50.80	1.83			6,000	39	234	0.058	0.625	9.55	0.035	0.004	1.057	14.49	0.82	554	62	298	229	MG02072509
21	63.50	1.09			6,000	40	200	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	554	61	297	228	MG02072507
22	63.50	1.37			6,000	37	222	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	553	63	299	226	MG02072508
23	76.20	1.09			6,000	38	228	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	554	61	297	228	MG02072507
24	76.20	1.37			6,000	32	192	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	553	63	299	226	MG02072508
25	76.20	0.91			6,000	390	2,340	0.057	0.624	9.57	0.038	0.004	1.055	14.46	0.82	554	61	297	228	MG02072505
26	101.60	1.37			6,000	24	144	0.055	0.623	9.56	0.037	0.003	1.054	14.47	0.82	553	63	299	226	MG02072508

Manufactured by



Checked by

[Handwritten signature]

